

Material

**Rolyan® Kay-Splint III
Basic Control**

Temperature

⅝" (3.2mm) 160° to 170° F (70° to 75°C) water for 1 minute



Stretch

Moderate resistance

Time

⅝" (3.2mm) 4 to 6 minutes of working time

**LATEX
FREE**